



Corrosie classificatie volgens ISO 12944:2018

Beschermingsduur	Systeemnr.	Type	Product	laagdikte
C3				
1 - 7 jaren	1	AK	Transogard QD Primer 1.23	60 µm
		AK	Transogard ZF-50 96.50	40 µm
			Totaal	100 µm
	2	EP	Transpoxy Barrier 92.16	60 µm
		PUR	Transurethane Finish 93.65	40 µm
			Totaal	100 µm
	3	PA	Transocean Aspartic 80-75 96.43	100 µm
			Totaal	100 µm
	4	EP	Transofine Primer 1.04	60 µm
		AY	Transofine Finish 4.04	40 µm
			Totaal	100 µm
	5	PUR	Transurethane DTM 50 96.41	100 µm
			Totaal	100 µm
	6	EP	Transofine Primer 1.04	60 µm
		PUR	Transurethane Finish H2O	40 µm
			Totaal	100 µm

7 - 15 jaren	1	EP	Transpoxy Barrier 92.16	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	120 µm
	2	PA	Transocean Aspartic 80-75 96.43	120 µm
			Totaal	120 µm
	3	EP	Transofine Primer 1.04	60 µm
		PUR	Transurethane Finish H2O	60 µm
			Totaal	120 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

15 - 25 jaren	1	EP	Transpoxy Masterbond 94.67	120 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	180 µm
	2	EP	Transozinc RZ Epoxy Primer 91.79	40 µm
		EP	Transpoxy Mio Sealer 91.65	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	160 µm
	3	EP	Transofine Primer 1.04	70 µm
		EP	Transofine Special 3.04	70 µm
		AY	Transofine Finish 4.04	40 µm
			Totaal	180 µm
	4	EP	Transofine Primer 1.04	60 µm
		EP	Transofine Special 3.04	60 µm
		AY	Transurethane Finish H2O	60 µm
			Totaal	180 µm

> 25 jaren	1	EP	Transpoxy ZP Primer 91.61	80 µm
		EP	Transpoxy Barrier 92.16	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	240 µm
	2	EP	Transpoxy Masterbond 94.67	160 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Totaal	240 µm
	3	EP	Transozinc RZ Epoxy Primer 91.79	40 µm
		EP	Transpoxy Mio Sealer 91.65	80 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Totaal	200 µm

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com