



transocean coatings

Corrosie classificatie volgens ISO 12944:2018

Beschermingsduur	Systeemnr.	Type	Product	laagdikte
C5				
1 - 7 jaren	1	EP	Transpoxy Masterbond 94.67	120 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	180 µm
	2	EP	Transofine Primer 1.04	70 µm
		EP	Transofine Special 3.04	70 µm
		AY	Transofine Finish 4.04	40 µm
			Totaal	180 µm
	3	EP	Transofine Primer 1.04	60 µm
		EP	Transofine Special 3.04	60 µm
		AY	Transurethane Finish H2O	60 µm
			Totaal	180 µm

7 - 15 jaren	1	EP	Transpoxy Barrier 92.16	80 µm
		EP	Transpoxy Masterbond 94.67	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	240 µm
	2	EP	Transozinc Epoxy Primer 91.55	40 µm
		EP	Transpoxy Masterbond 94.67	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	200 µm
	3	EP	Transpoxy Intermediate 92.19	80 µm
		EP	Transpoxy Intermediate 92.19	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	240 µm
	4	EP	Transpoxy ZP Primer 96.61	80 µm
		EP	Transpoxy Barrier 92.16	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	240 µm
	5	PUR	Transurethane zinc 1.60	80 µm
		PA	Transocean Aspartic 80-75 96.43	160 µm
			Totaal	240 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

15 - 25 jaren	1	EP	Transpoxy Masterbond 94.67	120 µm
		EP	Transpoxy Masterbond 94.67	120 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Totaal	300 µm
	2	EP	Transozinc Epoxy Primer 91.55	40 µm
		EP	Transpoxy Masterbond 94.67	140 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Totaal	260 µm
	3	EP	Transpoxy Barrier 92.16	70 µm
		EP	Transpoxy Masterbond 94.67	170 µm
		PUR	Transurethane Shield 3.45S	55 µm
			Totaal	295 µm
	4	PUR	Transurethane zinc 1.60	80 µm
		EP	Transpoxy Mio Sealer 91.65	100 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Totaal	260 µm

>25 jaren	1	SI	Transozinc Silicate 1.52	60 µm
		EP	Transpoxy Mio Sealer 91.65	80 µm
		EP	Transpoxy Barrier 92.16	100 µm
		PUR	Transurethane Shield 3.45	80 µm
			Totaal	320 µm

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com