



transocean coatings

Corrosie classificatie volgens ISO 12944:2018

Beschermingsduur	Systeemnr.	Type	Product	laagdikte
Cx				
Cx	1	EP	Transozinc Epoxy Primer 1.55	50 µm
		EP	Transpoxy Masterbond BT 4.68	175 µm
		PUR	Transurethane Shield 3.45	75 µm
			Totaal	300 µm
	2	SI	Transozinc Silicate 1.47	60 µm
		EP	Transpoxy Masterbond BT 4.68	100 µm
		SX	Transpoxyl 3.70	120 µm
			Totaal	280 µm

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com