



transocean coatings

Corrosie classificatie volgens ISO 12944:2018

Immersie	Systeemnr.	Type	Product	laagdikte
Im 1 t/m Im 4				
Im 1 zoet water 15 – 25 jaren	1	EP	Transpoxy ZP-HB 96.61	80 µm
		EP	Transpoxy Masterbond 94.67	150 µm
		EP	Transpoxy Masterbond 94.67	150 µm
			Totaal	380 µm
	2	EP	Transozinc Epoxy Primer 91.55	40 µm
		EP	Transpoxy Mio Sealer 91.65	80 µm
		EP	Transpoxy Master Mio 94.46	120 µm
		EP	Transpoxy Master Mio 94.46	120 µm
			Totaal	360 µm
	3	EP	Transpoxy Masterbond 94.67	150 µm
		EP	Transpoxy Masterbond 94.67	150 µm
		PUR	Transurethane Shield 3.45S	90 µm
			Totaal	390 µm

Im 2 zeewater of brakwater 15 – 25 jaren	1	EP	Transpoxy ZP-HB 96.61	80 µm
		EP	Transpoxy Masterbond 94.67	150 µm
		EP	Transpoxy Masterbond 94.67	150 µm
			Totaal	380 µm
	2	EP	Transozinc Epoxy Primer 91.55	40 µm
		EP	Transpoxy Mio Sealer 91.65	80 µm
		EP	Transpoxy Master Mio 94.46	120 µm
		EP	Transpoxy Master Mio 94.46	120 µm
			Totaal	360 µm
	3	EP	Transpoxy Masterbond 94.67	150 µm
		EP	Transpoxy Masterbond 94.67	150 µm
		PUR	Transurethane Shield 3.45S	90 µm
			Totaal	390 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

Im3	1	EP	Transpoxy ZP-HB 96.61	80 µm
ondergronds		EPGF	Transpoxy Glasscoat 4.40	150 µm
15-25 jaren		EPGF	Transpoxy Glasscoat 4.40	150 µm
			Totaal	380 µm

	1	EP	Transpoxy ZP-HB 96.61	80 µm
		EP	Transpoxy Masterbond 94.67	150 µm
Im 4		EP	Transpoxy Masterbond 94.67	150 µm
Zeewater of			Totaal	380 µm
Brakwater + KB				
15 – 25 jaren	2	EP	Transozinc Epoxy Primer 91.55	40 µm
		EP	Transpoxy Mio Sealer 91.65	80 µm
		EP	Transpoxy Master Mio 94.46	120 µm
		EP	Transpoxy Master Mio 94.46	120 µm
			Totaal	360 µm

De hierboven vermelde systemen zijn voorbeeldsystemen. In veel gevallen wordt er gevraagd om specifieke eisen door een opdrachtgever en/of applicateur. Voor een op maat gemaakt advies kunt u zich wenden tot onze technische afdeling.

Versiedatum: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com