



Atmosphärische Korrosivitätskategorien gemäß ISO 12944:2018

Schutzdauern	System Nr.	Typ	Produkt	Schicht Dicke
C3				
1 - 7 Jahre	1	AK	Transogard QD Primer 1.23	60 µm
		AK	Transogard ZF-50 96.50	40 µm
			Gesamt Schicht Dicke	100 µm
	2	EP	Transpoxy Barrier 92.16	60 µm
		PUR	Transurethane Finish 93.65	40 µm
			Gesamt Schicht Dicke	100 µm
	3	PA	Transocean Aspartic 80-75 96.43	100 µm
			Gesamt Schicht Dicke	100 µm
	4	EP	Transofine Primer 1.04	60 µm
		AY	Transofine Finish 4.04	40 µm
			Gesamt Schicht Dicke	100 µm
	5	PUR	Transurethane DTM 50 96.41	100 µm
			Gesamt Schicht Dicke	100 µm
	6	EP	Transofine Primer 1.04	60 µm
		PUR	Transurethane Finish H2O	40 µm
			Gesamt Schicht Dicke	100 µm

7 - 15 Jahre	1	EP	Transpoxy Barrier 92.16	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	120 µm
	2	PA	Transocean Aspartic 80-75 96.43	120 µm
			Gesamt Schicht Dicke	120 µm
	3	EP	Transofine Primer 1.04	60 µm
		PUR	Transurethane Finish H2O	60 µm
			Gesamt Schicht Dicke	120 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

15 - 25 Jahre	1	EP	Transpoxy Masterbond 94.67	120 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	180 µm
	2	EP	Transozinc RZ Epoxy Primer 91.79	40 µm
		EP	Transpoxy Mio Sealer 91.65	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	160 µm
	3	EP	Transofine Primer 1.04	70 µm
		EP	Transofine Special 3.04	70 µm
		AY	Transofine Finish 4.04	40 µm
			Gesamt Schicht Dicke	180 µm
	4	EP	Transofine Primer 1.04	60 µm
		EP	Transofine Special 3.04	60 µm
		AY	Transurethane Finish H2O	60 µm
			Gesamt Schicht Dicke	180 µm

> 25 Jahre	1	EP	Transpoxy ZP Primer 91.61	80 µm
		EP	Transpoxy Barrier 92.16	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	240 µm
	2	EP	Transpoxy Masterbond 94.67	160 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Gesamt Schicht Dicke	240 µm
	3	EP	Transozinc RZ Epoxy Primer 91.79	40 µm
		EP	Transpoxy Mio Sealer 91.65	80 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Gesamt Schicht Dicke	200 µm

Bei den oben aufgeführten Systemen handelt es sich um Beispielsystemen. In vielen Fällen werden von einem Kunden und/oder Anwender spezifische Anforderungen gestellt. Für eine individuelle Beratung wenden Sie sich bitte an unsere technische Abteilung

Stand: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com