



Atmosphärische Korrosivitätskategorien gemäß ISO 12944:2018

Schutzdauern	System Nr.	Typ	Produkt	Schicht Dicke
C5	Hot dip galvanized steel /Thermal sprayed steel			
1 - 7 Jahre	1	EP	Transpoxy ZP Primer 91.61	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	120 µm
	2	EP	Transpoxy Mio Sealer 91.65	60 µm
		PUR	Transurethane Finish Mio 93.65	60 µm
			Gesamt Schicht Dicke	120 µm
	3	EP	Transpoxy Mio Sealer 91.65	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	120 µm

7 - 15 Jahre	1	EP	Transpoxy ZP Primer 91.61	80 µm
		PUR	Transurethane Shiel 3.45S	80 µm
			Gesamt Schicht Dicke	160 µm
	2	EP	Transpoxy Mio Sealer 91.65	80 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Gesamt Schicht Dicke	160 µm

15 - 25 Jahre	1	EP	Transpoxy ZP Primer 91.61	70 µm
		EP	Transpoxy Barrier 92.16	70 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	200 µm
	2	EP	Transpoxy Mio Sealer 91.65	70 µm
		EP	Transpoxy Barrier 92.16	70 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	200 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVF) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

>25 Jahre	1	EP	Transpoxy Mio Sealer 91.65	80 µm
		EP	Transpoxy Barrier 92.16	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Gesamt Schicht Dicke	240 µm
	2	EP	Transpoxy Mio Sealer 91.65	110 µm
		PA	Transocean Aspartic 80-75 96.43	200 µm
			Gesamt Schicht Dicke	310 µm

Bei den oben aufgeführten Systemen handelt es sich um Beispielsystemen. In vielen Fällen werden von einem Kunden und/oder Anwender spezifische Anforderungen gestellt. Für eine individuelle Beratung wenden Sie sich bitte an unsere technische Abteilung

Stand: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com