

transocean coatings

Atmospheric corrosivity categories in accardance with ISO 12944:2018

| Durability | Systemnr. | Type | Product | DFT |
|--------------|-----------|----------|---------------------------------|------------------|
| C1 / C2 | | | | |
| | 1 | AK | Transogard QD Primer 1.23 | 80 µm |
| | | | Total | 80 µm |
| 1 - 7 years | | | | |
| | 2 | EP | Transpoxy Barrier 92.16 | 80 µm |
| | | | Total | 80 µm |
| | 3 | EP | Transofine Primer 1.04 | 70 µm |
| | · · | <u> </u> | Total | 70 µm |
| | | | rotai | 70 pm |
| | 4 | PUR | Transurethane DTM 50 96.41 | 80 µm |
| | | | Total | 80 µm |
| | | | | |
| | 1 | AK | Transogard QD Primer | 60 µm |
| | | AK | Transogard ZF-50 96.50 | 40 µm |
| 7 - 15 years | | | Total | 100 µm |
| | 2 | EP | Transpayy Parrier 02 16 | 100 um |
| | 2 | CF | Transpoxy Barrier 92.16 Total | 100 μm 100 μm |
| | | | i Oldi | 100 μπ |
| | 3 | EP | Transofine Primer 1.04 | 60 µm |
| | | AY | Transofine Finish 4.04 | 40 μm |
| | | | Total | 100 µm |
| | | | | |
| | 4 | EP | Transofine Primer 1.04 | 60 µm |
| | | PUR | Transurethane Finish H2O | 40 µm |
| | | | Total | 100 µm |
| | | | | |
| | 5 | PA | Transocean Aspartic 80-75 96.43 | 100 µm |
| | | | Total | 100 µm |
| | 6 | PUR | Transurethane DTM 50 96.41 | 100 µm |
| | - J | I OIX | Total | 100 μm |



| | 1 | EP | Transpoxy HS Primer 91.81 | 120 µm |
|---------------|---|-----|---------------------------------|--------|
| | | | Total | 120 µm |
| 15 - 25 years | | | | · |
| , | 2 | EP | Transpoxy Barrier 92.16 | 60 µm |
| | | PUR | Transurethane Shield 3.45S | 60 µm |
| | | | Total | 120 µm |
| | | | | · |
| | 3 | AY | Transogard QD Primer 1.23 | 80 µm |
| | | AY | Transogard ZF-50 96.50 | 80 µm |
| | | | Total | 160 µm |
| | | | | |
| | 4 | PA | Transocean Aspartic 80-75 96.43 | 120 µm |
| | | | Total | 120 µm |

| | 1 | EP | Transpoxy Masterbond 94.67 | 120 µm |
|------------|---|-----|----------------------------------|--------|
| | | PUR | Transurethane Shield 3.45S | 60 µm |
| | | | Total | 180 µm |
| > 25 years | | | | |
| | 2 | EP | Transozinc RZ Epoxy Primer 91.79 | 40 µm |
| | | EP | Transpoxy Mio Sealer 91.65 | 60 µm |
| | | PUR | Transurethane Shield 3.45S | 60 µm |
| | | | Total | 160 µm |

Listed coating systems are some examples of typical environments. Nevertheless, detailed coating systems can be made, based on detailed information. Please consult our technical department.

Issue date: 1-2-2024

