



transocean coatings

Atmospheric corrosivity categories in accordance with ISO 12944:2018

Durability	Systemnr.	Type	Product	DFT
C3	Hot dip galvanized steel /Thermal sprayed steel			

15 - 25 years	1	EP	Transpoxy ZP Primer 91.61	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Total	120 µm
	2	EP	Transpoxy Mio Sealer 91.65	60 µm
		PUR	Transurethane Finish Mio 93.65	60 µm
			Totaal	120 µm
> 25 years	3	EP	Transpoxy Mio Sealer 91.65	60 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Total	120 µm
	1	EP	Transpoxy ZP Primer 91.61	80 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Total	160 µm
> 25 years	2	EP	Transpoxy Mio Sealer 91.65	80 µm
		PUR	Transurethane Finish Mio 93.65	80 µm
			Total	160 µm
	3	EP	Transpoxy Mio Sealer 91.65	80 µm
		PUR	Transurethane Shield 3.45S	80 µm
			Total	160 µm

Listed coating systems are some examples of typical environments. Nevertheless, detailed coating systems can be made, based on detailed information. Please consult our technical department.

Issue date: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com