



transocean coatings

Atmospheric corrosivity categories in accordance with ISO 12944:2018

Durability	Systemnr.	Type	Product	DFT
C5				
1 - 7 years	1	EP	Transpoxy Masterbond 94.67	120 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Total	180 µm
	2	EP	Transofine Primer 1.04	70 µm
		EP	Transofine Special 3.04	70 µm
		AY	Transofine Finish 4.04	40 µm
			Total	180 µm
	3	EP	Transofine Primer 1.04	60 µm
		EP	Transofine Special 3.04	60 µm
		AY	Transurethane Finish H2O	60 µm
			Total	180 µm

7 - 15 years	1	EP	Transpoxy Barrier 92.16	80 µm
		EP	Transpoxy Masterbond 94.67	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Total	240 µm
	2	EP	Transozinc Epoxy Primer 91.55	40 µm
		EP	Transpoxy Masterbond 94.67	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Total	200 µm
	3	EP	Transpoxy Intermediate 92.19	80 µm
		EP	Transpoxy Intermediate 92.19	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Total	240 µm
	4	EP	Transpoxy ZP Primer 96.61	80 µm
		EP	Transpoxy Barrier 92.16	100 µm
		PUR	Transurethane Shield 3.45S	60 µm
			Total	240 µm
	5	PUR	Transurethane zinc 1.60	80 µm
		PA	Transocean Aspartic 80-75 96.43	160 µm
			Total	240 µm



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com

15 - 25 years	1	EP	Transpoxy Masterbond 94.67	120 µm
		EP	Transpoxy Masterbond 94.67	120 µm
		PUR	Transurethane Shield 3.45S	60 µm
		Total		300 µm
	2	EP	Transozinc Epoxy Primer 91.55	40 µm
		EP	Transpoxy Masterbond 94.67	140 µm
		PUR	Transurethane Shield 3.45S	80 µm
		Total		260 µm
	3	EP	Transpoxy Barrier 92.16	70 µm
		EP	Transpoxy Masterbond 94.67	170 µm
		PUR	Transurethane Shield 3.45S	55 µm
		Total		295 µm
	4	PUR	Transurethane zinc 1.60	80 µm
		EP	Transpoxy Mio Sealer 91.65	100 µm
		PUR	Transurethane Shield 3.45S	80 µm
		Total		260 µm

>25 years	1	SI	Transozinc Silicate 1.52	60 µm
		EP	Transpoxy Mio Sealer 91.65	80 µm
		EP	Transpoxy Barrier 92.16	100 µm
		PUR	Transurethane Shield 3.45	80 µm
		Total		320 µm

Listed coating systems are some examples of typical environments. Nevertheless, detailed coating systems can be made, based on detailed information. Please consult our technical department.

Issue date: 1-2-2024



All our offers, contracts, deliveries, services and all correspondence, including email, are subject to the General Terms and Conditions of Delivery from the branch organisation of the Paint Printing Ink Industry (VVFV) of 2003 which are deposited at the office of the Clerk of the District Court of Amsterdam; number and date on request. They are an integral part of all contracts that we conclude with our contractual partners for the deliveries and services we offer. Of the Uniform Sales conditions deviating purchasing conditions of the buyer will not be accepted by us. See Article 1 of the Uniform Sales conditions on www.zandleven.com