

transocean coatings

Atmospheric corrosivity categories in accordance with ISO 12944:2018

Durability	Systemnr.	Type	Product	DFT
Сх				

	1	EP	Transozinc Epoxy Primer 1.55	50 µm
		EP	Transpoxy Masterbond BT 4.68	175 µm
Сх		PUR	Transurethane Shield 3.45	75 µm
			Total	300 µm
	2	SI	Transozinc Silicate 1.47	60 µm
		EP	Transpoxy Masterbond BT 4.68	100 µm
		SX	Transpoxyl 3.70	120 µm
			Total	280 µm

Listed coating systems are some examples of typical environments. Nevertheless, detailed coating systems can be made, based on detailed information. Please consult our technical department.

Issue date: 1-2-2024

